
On the light refraction and polarisation in the presence of weak optical activity

Zapeka B., Kostyrko M. and Vlokh R.

Institute of Physical Optics, 23 Dragomanov St., 79005 Lviv, Ukraine,
e-mail: vlokh@ifp.lviv.ua

Received: 30.01.2010

Abstract

We show that the weak optical activity should manifest itself in changing refractive indices and optical birefringence of a medium. Increments of both the refractive indices and the birefringence which appear due to the weak optical activity are quite small and depend on the signs of neither the optical activity vector nor the light wave vector.

Keywords: weak optical activity, gyration, spatial dispersion, refraction, polarisation

PACS: 78.20.Ek

UDC: 535.56

1. Introduction

It is well known that the optical activity is described by accounting of inhomogeneity of electric induction D_j in relation to electric field E_i of an optical wave propagating through a medium:

$$E_i = B_{ij}^0 D_j + i\gamma_{ijk} \frac{\partial D_j}{\partial x_k}, \quad (1)$$

where B_{ij}^0 denotes the optical-frequency impermeability tensor, γ_{ijk} third-rank antisymmetric polar tensor ($\gamma_{ijk} = -\gamma_{jik}$) and x_k the coordinate. Using the known duality relation,

$$\frac{2\pi}{\lambda} \gamma_{ijk} = \delta_{ijl} g_{lk}, \quad (2)$$

one can write the tensor γ_{ijk} as an axial nonsymmetric second-rank gyration tensor g_{lk} (with δ_{ijl} being the unit antisymmetric Levi-Civita tensor). Thus, Eq. (1) may be rewritten as

$$E_i = (B_{ij}^0 + i\delta_{ijl} g_{lk} m_k) D_j, \quad (3)$$

where $k_k = \frac{2\pi}{\lambda} m_k$ is the wave vector of light and m_k the unit vector parallel to k_k . The nonsymmetric gyration tensor may be decomposed in the symmetric and antisymmetric parts:

$$g_{lk} = g_{lk}^s + g_{lk}^{as}, \quad (4)$$

A common point of view is that the optical activity effect is purely associated with the symmetric part of the gyration tensor. Concerning its antisymmetric part which is dual to some polar vector h_r ,

$$g_{lk}^{as} = \delta_{lkr} h_r, \quad (5)$$

and describes a so-called weak optical activity [1], only a few mentions may be found in the literature. As far as we know, the latter phenomenon has not yet been discovered. However, some data are available in the literature on the observation of this effect by indirect optical techniques, i.e. by changes observed in the exciton reflection and luminescence spectra [2, 3]. It has been shown in the work [4] that the weak optical activity can be detected by ellipsometric analysis of the light reflected from relevant gyrotropic crystals. Moreover, it has been stated in [5] that the reflection spectroscopy is the only method enabling any experimental studies of the weak optical activity. Besides, as mentioned in the work [6], this kind of optical activity should cause no changes in the refractive indices of weakly optically active media.

The present work is devoted to description of weak optical activity in crystals and analysis of manifestations of this phenomenon.

2. Polarisation of optical waves

Let us consider the weak optical activity in a more detail. Since the vector h_r is a constitutive coefficient of a medium, its non-zero value would be peculiar only of polar media. Actually, the point symmetry groups for which $h_r \neq 0$ are 1, 2, m , $mm2$, 3, $3m$, 4, $4mm$, 6, $6mm$, ∞ and ∞mm . Among these groups, only four do not reveal the usual optical activity ($g_{lk}^s = 0$), namely $3m$, $4mm$, $6mm$ and ∞mm . For those media Eq. (3) may be written as

$$E_i = \left(B_{ij}^0 + i \delta_{ijl} \delta_{lkr} [h_r \times m_k] \right) D_j. \quad (6)$$

It is obvious that only a single component of the h_r vector remains non-zero for the crystals belonging to the point groups $3m$, $4mm$, $6mm$, e.g., $h_3 \neq 0$. Hence, the waves propagating along Z axis should not be affected by the weak optical activity because the vector product is $[h_3 \times m_3] = 0$ in this case.

Notice that the imaginary part of the optical-frequency impermeability tensor $i \delta_{ijl} \delta_{lkr} [h_r \times m_k]$ is antisymmetric either for the usual or weak optical activity effects, being dual to an axial vector. For example, for the propagation of light along X axis we may write

$$E_i = \left(B_{ij}^0 + i \delta_{ij2} \delta_{213} [h_3 \times m_1] \right) D_j, \quad (7)$$

where the indices i, j are equal to 1, 3 or 3, 1, respectively. Then we have

$$E_1 = (B_{13}^0 + i\delta_{132}\delta_{213}[h_3 \times m_1])D_3 \quad \text{or} \quad (8)$$

$$E_3 = (B_{31}^0 + i\delta_{312}\delta_{213}[h_3 \times m_1])D_1$$

Since $B_{31}^0 = B_{13}^0 = 0$ and $\delta_{312} = 1$, $\delta_{213} = -1$, $\delta_{132} = -1$, one can present Eqs. (8) as

$$\Delta E_1 = E_1 - B_{13}^0 D_3 = [i[h_3 \times m_1] \times D_3] \quad \text{or} \quad (9)$$

$$\Delta E_3 = E_3 - B_{31}^0 D_1 = [-i[h_3 \times m_1] \times D_1]$$

where $[h_3 \times m_1] = \rho_2$ is an axial vector describing rotation of the E_i vector around Y axis with respect to the D_j vector, i.e.

$$\Delta E_1 = i[\rho_2 \times D_3] \quad \text{or} \quad \Delta E_3 = -i[\rho_2 \times D_1]. \quad (10)$$

Thus, the weak optical activity should manifest itself in appearance of a so-called longitudinal component of the electric field of electromagnetic wave and a longitudinal ellipticity of extraordinary wave (see Figure 1).




Fig. 1. Schematic representation of electric field components of electromagnetic wave in the presence of weak optical activity (a, b) and ellipticity of one of the eigen waves for this case (c).

It is seen from the above relations that during each half period the wave becomes purely longitudinal with respect to the wave vector k_1 , though the latter conclusion is not novel (see, e.g., [1, 7]). Furthermore, the electromagnetic wave can have only a transverse polarisation due to the well-known relations $(D \cdot k) = 0$ and $(E \cdot S) = 0$ (with S being the Poynting vector). At this point a number of questions appear, e.g., how the Poynting vector is directed for this longitudinal electric field component of the wave, and whether the weak optical activity influences the refractive indices of the medium?

3. Refractive indices and the ellipticity of light

Let us consider the case of optically uniaxial crystals, for which the following conditions are satisfied:

$$h_3 \neq 0, h_1 = h_2 = 0, \quad B_{11}^0 = B_{22}^0 \neq B_{33}^0, \quad m_2 = m_3 = 0, \quad m_1 = 1. \quad (11)$$

The matrix that couples the components of the electric field and electric displacement vectors may be given by

$$\begin{array}{c|ccc} & D_1 & D_2 & D_3 \\ \hline E_1 & B_{11}^0 & 0 & i\rho_2 \\ E_2 & 0 & B_{11}^0 & 0 \\ E_3 & -i\rho_2 & 0 & B_{33}^0 \end{array}, \quad (12)$$

so that we get a system of equations in the following form:

$$\begin{cases} E_1 = B_{11}^0 D_1 + [i[h_3 \times m_1] \times D_3] \\ E_2 = B_{11}^0 D_2 \\ E_3 = [-i[h_3 \times m_1] \times D_1] + B_{33}^0 D_3 \end{cases}. \quad (13)$$

As one can easily see, the refractive index for the wave polarised parallel to the Y axis remains unchanged and is equal to $n_2 = 1/\sqrt{B_{11}^0}$. Accounting for that $E_1 = D_1/n^2$ and $E_3 = D_3/n^2$, one can reduce the system of Eqs. (13) to that including only two equations:

$$\begin{cases} \frac{D_1}{n^2} = B_{11}^0 D_1 + [i[h_3 \times m_1] \times D_3] \\ \frac{D_3}{n^2} = [-i[h_3 \times m_1] \times D_1] + B_{33}^0 D_3 \end{cases}, \quad (14)$$

or

$$\begin{cases} \left(\frac{1}{n^2} - \frac{1}{n_{01}^2} \right) D_1 - [i[h_3 \times m_1] \times D_3] = 0 \\ [i[h_3 \times m_1] \times D_1] + \left(\frac{1}{n^2} - \frac{1}{n_{03}^2} \right) D_3 = 0 \end{cases}. \quad (15)$$

This system has two positive roots:

$$n_3 = n_{03} - \frac{1}{4} \frac{n_{03}^6}{\Delta n_{13}} [h_3 \times m_1]^2 \quad (16)$$

and

$$n_1 = n_{01} - \frac{1}{4} \frac{n_{01}^6}{\Delta n_{13}} [h_3 \times m_1]^2, \quad (17)$$

with

$$\Delta n_{32} = n_3 - n_2 = \Delta n_{32}^0 - \frac{1}{4} \frac{n_{03}^6}{\Delta n_{13}} [h_3 \times m_1]^2. \quad (18)$$

Hence, the ellipticity κ of the extraordinary eigen wave is defined by the relation

$\frac{D_1}{D_3} = i\kappa$, and we obtain

$$\kappa = \frac{[h_3 \times m_1]^2}{\frac{1}{n_{03}^2} - \frac{1}{n_{01}^2}} = \frac{\bar{n}^3 [h_3 \times m_1]^2}{2\Delta n_{13}^0} \quad \text{or} \quad \kappa = \frac{\bar{n}^3 h_3^2}{2\Delta n_{13}^0}, \quad (19)$$

where \bar{n} is the mean refractive index and Δn_{13}^0 the initial birefringence. The ellipticity of the ordinary eigen wave remains to be zero. The relation for the optical retardation may be represented as

$$\Delta = \frac{2\pi d}{\lambda} \Delta n_{32} = \frac{2\pi d}{\lambda} \left(\Delta n_{32}^0 - \frac{1}{4} \frac{n_{03}^6}{\Delta n_{13}} [h_3 \times m_1]^2 \right). \quad (20)$$

Here we have taken into account that the two electric field components (E_3 and E_1) of the electromagnetic wave appear in the presence of weak optical activity when the incident light propagates along the X direction in crystals or textures belonging to the point symmetry groups $3m$, $4mm$, $6mm$ and ∞mm . The corresponding components of the Poynting vectors are defined by the relations

$$S_1 = [E_3 \times H_2], \quad (21)$$

and

$$S_3 = [E_1 \times H_2]. \quad (22)$$

Thus, the electromagnetic energy flow could appear along the Z axis at the cost of reducing the corresponding energy flux along the X axis. This problem will be discussed in our forthcoming papers, along with the problem of parameters of electromagnetic waves in case of coexisting symmetric and antisymmetric parts of the gyration tensor (i.e., both coexisting “strong” and weak optical activities).

Conclusions

From the relations derived above a number of important conclusions follow. The first is that the weak optical activity should manifest itself in some changes of the refractive in-

dices and the birefringence. The second is that the increments of the refractive indices and the optical birefringence appearing due to the weak optical activity do not depend on the sign of h_3 vector, and the same concerns the sign of the wave vector m_1 . Notice that the signs of the rotation of polarisation plane or the phase difference caused by the usual optical activity depend on the wave vector sign.

Finally, the increments of both the refractive indices and the birefringence caused by the weak optical activity are very small, being proportional to the square of the optical activity vector (h_r^2). Indeed, assuming that the antisymmetric part of the gyration tensor is of the same order of magnitude as the symmetric one ($\sim 10^{-5}$ in common cases), we arrive at the conclusion that the birefringence increment should be of the order of 10^{-7} . The ellipticity of the eigen extraordinary wave in this case should also be very small ($\sim 10^{-7}$).

References

1. Fedorov F I, 1959. On the theory of optical activity of crystals. 2. Crystals of cubic system and polar classes of middle systems. Opt. Spektrosk. **6**: 377–383.
2. Ivchenko E I, Permogorov S A and Selkin A V, 1978. Reflection of light with a change of polarization state from the real crystal boundary. Sol. St. Commun. **28**: 345–348.
3. Ivchenko E L, Pevtsov A B and Sel'kin A V, 1981. Effects of optical activity on exciton luminescence of CdS. Sol. St. Commun. **39**: 453–455.
4. Zil'bershtein A Kh and Solov'ev L E, 1998. Reflection of light with a change of polarization state from real crystal boundary. Opt. Spectr. **84**: 549–552.
5. Lalov I J and Kojouharova N A, 2000. Reflection of electromagnetic waves at the boundary of optically active media. Bulgarian J. Phys. **27**: 66–71.
6. Agranovich V M and Ginzburg V L. Crystal optics with spatial dispersion, and excitons (2nd edition). Moscow: Nauka (1979).
7. Sirotin Yu I and Shaskolskaya M P. Fundamentals of crystal physics. Moscow: Nauka (1979).

Zhang Jia, Hong Sang-Jin and Seo Dong-Sun, 2010. On the light refraction and polarisation in the presence of weak optical activity. Ukr.J.Phys.Opt. **11**: 68-73.

Анотація. Показано, що слабка оптична активність повинна виявлятися у змінах показників заломлення і двозаломлення середовища. Прирости показників заломлення і двозаломлення, що з'являються внаслідок слабкої оптичної активності, досить малі і не залежать ні від знака вектора оптичної активності, ні від знака хвильового вектора світла.